


NUMBER : DELH21014778 DATE : 31ST OCT, 2021



ORIGINAL SAMPLE

Page 1 of 5

Tel: 0124-4503400,

Fax: 0124-4303592 www.Intertek.com





NUMBER: DELH21014778 DATE : 31ST OCT, 2021

SAMPLE DESCRIPTION

: ICE TONG

DATE RECEIVED

: 27TH OCT, 2021

BUYER

BUYING AGENT

: --

STYLE NO.

ORDER NO

COLOR

END USE

: STAINLESS STEEL ARTICLE FOR FOOD STUFF

MATERIAL CONTENT

: --

SEASON

COUNTRY OF DESTINATION COUNTRY OF ORIGIN

MANUFACTURER'S NAME

TESTS CONDUCTED: AS REQUESTED BY THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO THE ENCLOSED PAGE (S).

CONCLUSION:

TESTED SAMPLE	<u>STANDARD</u>	RESULT
SUBMITTED SAMPLE	COUNCIL OF EUROPE RESOLUTION CM/RES (2013)9 ON METALS AND ALLOYS USED IN FOOD CONTACT MATERIALS AND ARTICLES ACC. TO ART. 3 OF (EC)1935/2004 REGULATION	
	ODOUR TEST & SENSORY TEST (LFGB SECTION 30 & 31 /DIN- 10955)	M

NOTE: M = MEET CLIENT'S REQUIREMENT # = NO SPECIFIED REQUIREMENT

F = BELOW CLIENT'S REQUIREMENT N/A = NOT APPLICABLE

FOR INTERTEK INDIA PVT. LTD

Stodame SANJAY SADANA

TECHNICAL MANAGER - HARDLINE

Page 2 of 5



NUMBER : DELH21014778 DATE : 31ST OCT, 2021

TEST CONDUCTED:

1. SPECIFIC MIGRATION OF HEAVY METAL:

(COUNCIL OF EUROPE RESOLUTION CM/RES (2013)9 ON METALS AND ALLOYS USED IN FOOD CONTACT MATERIALS AND ARTICLES ACC. TO ART. 3 OF (EC) 1935/2004 REGULATION)

TEST CONDITIONS: ARTIFICIAL TAP WATER AT ROOM TEMP. FOR 30 MIN.

TESTED COMPONENT: ICE TONG

ELEMENT	RESULT (mg/kg food) AFTER 1st + 2nd MIGRATION	REQUIREMENT (mg/kg food)	
	CYCLE		
SILVER (AG)	<0.1	0.56	
ALUMINIUM (AL)	<2	35	
COBALT(CO)	<0.02	0.14	
CHROMIUM(CR)	<0.2	1.75	
COPPER (CU)	<2.0	28	
IRON(FE)	<10	280	
MAGNESIUM(MG)	<2	-	
MANGANESE(MN)	<0.2	12.6	
MOLYBDENUM(MO)	<0.2	0.84	
NICKEL(NI)	<0.2	0.98	
TIN(SN)	<10	700	
TITANIUM(TI)	<0.2	_	
VANADIUM(V)	<0.02	0.070	
ZINC(ZN)	<10	35	
ARSENIC(AS)	<0.002	0.014	
BARIUM(BA)	<0.2	8.4	
BERYLIUM(BE)	<0.02	0.07	
CADMIUM(CD)	<0.002	0.035	
MERCURY(HG)	<0.002	0.021	
LITHIUM(LI)	<0.002	0.336	
LEAD(PB)	<0.002	0.070	
ANTIMONY(SB)	<0.02	0.28	
THALLIUM(TL)	<0.0002	0.0007	

Page 3 of 5





NUMBER : DELH21014778 DATE : 31ST OCT, 2021

TEST CONDITIONS: ARTIFICIAL TAP WATER AT ROOM TEMP. FOR 30 MIN.

3RD Attack Result

ELEMENT	RESULT (mg/kg food)	REQUIREMENT (mg/kg food)
SILVER (AG)	<0.01	0.08
ALUMINIUM (AL)	<1	5
COBALT(CO)	<0.01	0.02
CHROMIUM(CR)	<0.1	0.250
COPPER (CU)	<1	4
IRON(FE)	<5	40
MAGNESIUM(MG)	<1	-
MANGANESE(MN)	<0.1	1.8
MOLYBDENUM(MO)	<0.1	0.12
NICKEL(NI)	<0.1	0.14
TIN(SN)	<5	100
TITANIUM(TI)	<0.1	-
VANADIUM(V)	<0.01	0.01
ZINC(ZN)	<5	5
ARSENIC(AS)	<0.001	0.002
BARIUM(BA)	<0.10	1.2
BERYLIUM(BE)	<0.01	0.01
CADMIUM(CD)	<0.001	0.005
MERCURY(HG)	<0.001	0.003
LITHIUM(LI)	<0.001	0.048
LEAD(PB)	<0.001	0.010
ANTIMONY(SB)	<0.01	0.04
THALLIUM(TL)	<0.0001	0.0001

n



NUMBER: DELH21014778 DATE : 31ST OCT, 2021

2. ODOUR TEST & SENSORY TEST:

METHOD: (LFGB SECTION 31 /DIN- 10955)

TEST CONDITIONS AND RESULTS:

ODOUR TEST:

SIMULANT USED: WATER TEMPERATURE: ROOM TEMP.

TIME: 30 MIN.

SENSORY TEST

SIMULANT USED: WATER TEMPERATURE: ROOM TEMP.

TIME: 30 MIN.

TESTED SAMPLE	RESULT	LIMIT
SUBMITTED SAMPLE	COMPLIES ODOUR: Grade: 0 SENSORY: Grade: 0	Grade: ≤2.5

ODOUR GRADE LIST:

- 0= NO PERCEPTIBLE OFF ODOUR 1= OFF ODOUR JUST PERCEPTIBLE 2= SLIGHT OFF ODOUR 3= DISTINCT OFF ODOUR
- 4= STRONG OFF ODOUR.

SENSORY GRADE LIST:

- 0= NO PERCEPTIBLE OFF IN TASTE 1= JUST PERCEPTIBLE DIFFERENCE IN TESTE (STILL DIFFICULT TO DEFINE)
- 2= WEAK DIFFERENCE IN TASTE 3= MARKED DIFFERENCE IN TASTE
- 4= STRONG DIFFERENCE IN TASTE

TESTED COMPONENT:

A. ICE TONG

END OF TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis, and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

Page 5 of 5